

Technical Data Sheet

Choice Sky White PRSF 80005

Description: Thermosetting polyester TGIC powder coating. Polyester TGIC's are designed for interior

or exterior applications.

Typical Applications: General metals, architectural, automotive, lawn & garden furniture, stadium seating, light

fixtures, marine, fencing, etc.

Typical Film Thickness 1.7-3.0+ mil

Physical Properties: Gloss 60'angle (ASTM D-523-89) 90+

 $\begin{array}{lll} \text{Hardness (ASTM D-3363-92A)} & \text{H}-2\text{H} \\ \text{Flexibility (ASTM D-1737-89)} & 1/8 \text{ inch} \\ \text{Adhesion (ASTM D-3359-95A)} & 5b (100\%) \\ \text{Impact Direct/Indirect (ASTM D-2794-93)} & 160 \text{ in-lbs} \\ \text{Exterior Durability} & \text{Very Good} \\ \text{Chemical Resistance} & \text{Good} \\ \end{array}$

Salt Spray (ASTM B117) 1000 Hrs < 1/8'

Specific Gravity (calculated) 1.64

Application Data: Polyester TGIC's are to be applied with a corona electrostatic powder spray gun at

between 60kv - 100 kv.

Cure Schedule: Polyester TGIC's can be cured in a direct or indirect gas convection oven, an electric

oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 10 Minutes @ 400°f Peak Metal Temperature

Storage: Product should be stored at temperatures below 80°f, in a dry area away from any heat

source.

Notes: All tests were performed on Bonderite 1000, iron phosphated panels with a nominal film

thickness of 2 mils.

Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.